TAIYO AMERICA, INC. 2675 Antler Drive, Carson City, NV 89701

Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with the manufacturing specifications for this product.

This product meets all the requirements of Bellcore GR-78-CORE Issue 1, September 1997 for Legend and Marking Inks.

Lot # 1110937 Mfg. Date: 11-09-21 Warranty Ends: 8-09-22 UVR-110W (USA) **MANUFACTURING PROPERTY SPECIFICATION TEST METHOD** RESULT VISCOSITY Toki Sangyo RE100U Viscometer 116 ps 5 rpms @ 25°C 110 - 130 ps THIXOTROPIC INDEX Toki Sangyo RE100U Viscometer 1.8 Viscosity ratio: 5 rpm / 50 rpm 1.5 - 2.5FINENESS OF GRIND 7.5 microns TAI-0-0002 17.5 microns maximum VISUAL EXAMINATION Microscopic examination: Passed | 1. 1-mil drawdown of wet film No bubbles, pits, voids, particles, color differences. 2. Wet film drawdown on Passed No bubbles, pits, voids, grind gauge particles, color differences. **SCREENABILITY** Passed Visual inspection of coated panel No surface defects, such as bubbles, pinholes, etc. HH PENCIL HARDNESS (*) TAI-0-0020 3H or greater ADHESION (*) Passed V TAI-0-0021 100/100 on copper

(*) - UV cure for these tests was 1.0 joules/cm² as measured by a ORC UV-350 radiometer using three high pressure mercury vapor lamps @ 80 W/cm.

Verified By:

Q.C. SUPERVISOR 11/11/21

FRM-0-0009

7/13/01