## TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

## CERTIFICATE OF CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with the manufacturing specifications for this product.

PIHP-200 Part A

grind gauge

Lot # 9052037 Mfg. Date: 5-20-19 Warranty Ends: 5-20-20

		M	ANUFACTURING	
PROPERTY	TEST METHOD		<b>SPECIFICATION</b>	RESULT
VISCOSITY	Toki Sangyo RE100U Viscometer		Before mixing: Report Only	475 ps
	5 rpms @ 25°C		After mixing: 250 - 270 ps	253 ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm		After mixing: 2.0 - 2.5	2,2
FINENESS OF GRIND	TAI-0-0002		25 microns maximum	12.5 microns
VISUAL EXAMINATION	Microscopic examination:  1. 1-mil drawdown of wet film		No bubbles, pits, voids, particles, color differences.	Passed 🔽
	2. Wet film drawdown on		No bubbles, pits, voids,	Passed

particles, color differences.

FRM-0-0087

11/6/03