TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

This product meets all the requirements of IPC-SM-840E Classes H and T and Bellcore (Telecordia) GR-78-CORE.

Lot# 9032747 Mfg. Date: 3-27-19 UVR-150 TU Green Warranty Ends: 3-27-20 MANUFACTURING RESULT **SPECIFICATION TEST METHOD PROPERTY** Toki Sangyo RE100U Viscometer 120 - 140 ps 5 rpms @ 25°C THIXOTROPIC INDEX Toki Sangyo RE100U Viscometer 1.3 - 1.9Viscosity ratio: 5 rpm / 50 rpm microns FINENESS OF GRIND 17.5 microns maximum TAI-0-0002 VISUAL EXAMINATION Microscopic examination: Passed No bubbles, pits, voids, 1. 1-mil drawdown of wet film particles, color differences. Passed No bubbles, pits, voids, 2. Wet film drawdown on particles, color differences. grind gauge Passed **SCREENABILITY** No surface defects. Visual inspection of coated panel such as bubbles, pinholes, etc. Passed V RESISTANCE TO 260°C (500°F) / 10 sec x 3 cycles No discoloration, peeling, **SOLDERING (*)** Rosin-based flux or blistering Passed No swelling, softening, **SOLVENT** Immersion in PM Acetate **RESISTANCE** (*) 20°C / 30 mins. or blistering PENCIL HARDNESS (*) 4H or greater TAI-0-0020 Passed ADHESION (*) 100/100 on copper TAI-0-0021

(*) – UV cure for these test was 1.0 joules/cm² as measured by a ORC UV-350 radiometer using three high pressure mercury vapor lamps @ 80 w/cm.

Verified By:

A.C. SUPERVISOR 3/29/19

Name, Title, Date