TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with the manufacturing specifications for this product.

TER-20 K27

Lot# 9050137

Luis Marquez QC Supervisor Mfg. Date: 5-01-19
Warranty Ends: 11-01-19

PROPERTY VISCOSITY	TEST METHOD Toki Sangyo RE100U Viscometer	MANUFACTURING SPECIFICATION	RESULT
VISCOSIII	5 rpms @ 25°C	135 - 165 ps	138 ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	1.10 – 1.50	1,45
FINENESS OF GRIND	TAI-0-0002	15 microns maximum	5 microns
VISUAL EXAMINATIO	N Microscopic examination:		7
	1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed
	Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed
SCREENABILITY	Visual inspection of screen Printed panel	No surface defects,	Passed
TACK-DRY	Hot air convection oven $90^{\circ}\text{C} / 30 \text{ minutes}$	Tack-free to the touch	Passed
IMAGING	ORC HMW 680GW 7kW 100 mJ/cm ²	Stouffer step: Report Only (clear on copper)	H
,	Horizontal Developer – 1% Na2CO3 30°C (86°F) / 60 secs., 20 psi	A 10 10	
PENCIL HARDNESS	TAI-0-0020	H Minimum	H.
ADHESION	TAI-0-0021	100/100 on copper	Passed
STRIPPABILITY	TAI-0-0028	No ink residue	Passed D
w.	ARRANTY EXTENSION		. *
re Ai Ci ar	nis product has been tested by the Taiyo merica Quality ontrol department nd has been granted warranty extension.	Verified By: H. O.C. Superv	1300 5/3/19 Date
W	arranty period ends:	Name, Title,	Date
FRM-0-0170	12/01/19		10/9/09
Au	thorized By:		₩.