TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

PSR-4000 HPG Lo	ot# 1110887	Mfg. Date: \(\(\) - 0 \(\) Warranty Ends: \(\) 5 - 0	-21 18-22	
PROPERTY VISCOSITY	TEST METHOD Toki Sangyo RE100U Viscometer 5 rpms @ 25°C	MANUFACTURING SPECIFICATION Before mixing: 205 - 255 ps After mixing: 135 - 165 ps	<u>RESU</u> 239	
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	After mixing: 1.2 - 1.8	1.6	
FINENESS OF GRIND	TAI-0-0002	5 microns maximum	5 i	nicrons
VISUAL EXAMINATION	Microscopic examination:			
	1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed	P
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed	ď
SCREENABILITY	Visual inspection of screen printed panel	No surface defects, such as bubbles, pinholes, etc.	Passed	U
TACK-DRY	Hot air convection oven 80°C / 30 minutes	Tack-free to the touch	Passed	ď
IMAGING	ORC HMW 680GW - 7 kW 300 mJ / cm ²	Report Only (clear on copper)	10	
	Horizontal Developer - 1% Na2CO3 30°C (86°F) / 60 secs., 28 psi			
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 30 sec x 1 cycle Rosin-based flux	No discoloration, peeling, or blistering	Passed	V
SOLVENT RESISTANCE (*)	Immersion in PM Acetate 20°C / 20 mins.	No swelling, softening, or blistering	Passed	ď
PENCIL HARDNESS (*)	TAI-0-0020	5H or greater	9 H	•
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed	4

(*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven

Verified By	:	Sulsavisar	40/10/01
_XV:	Q.C.	JUISRVIJOR	14/19/21
Name,			Date

FRM-0-0147

1/28/09