TAIYO AMERICA, INC.
2675 Antler Drive, Carson City, NV 89701
Phone: (775) 885-9959   Fax: (775) 885-9972

CERTIFICATE OF CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with the manufacturing specifications for this product.

S-200Y NP (USA)　　　Lot # **9031847**　　　Mfg. Date: **3-18-19**
　　　　　　　　　　　　　　　　　　　　　　Warranty Ends: **9-18-19**

PROPERTY	TEST METHOD	MANUFACTURING SPECIFICATION	RESULT
VISCOSITY	Toki Sangyo RE100U Viscometer 5 rpms @ 25°C	Before mixing: 290 - 350 ps After mixing: *Report Only*	**298** ps **426** ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	Before mixing: 1.4 - 2.2 After mixing: *Report Only*	**1.8** **2.6**
FINENESS OF GRIND	TAI-0-0002	17.5 microns maximum	**5** microns
VISUAL EXAMINATION	Microscopic examination: 1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed ☑
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed ☑
SCREENABILITY	Visual inspection of coated panel	No surface defects, such as bubbles, pinholes, etc.	Passed ☑
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 10 sec x 2 cycles Rosin-based flux	No discoloration, peeling, or blistering	Passed ☑
SOLVENT RESISTANCE (*)	Immersion in PM Acetate 20°C / 30 mins.	No swelling, softening, or blistering	Passed ☑
PENCIL HARDNESS (*)	TAI-0-0020	7H or greater	**9H**
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed ☑

(*) - Final cure for these tests was 20 minutes @ 140°C (284°F) in a convection oven

WARRANTY EXTENSION
This product has been retested by the Taiyo America Quality Control department and has been granted a warranty extension.

Warranty period ends:

_____10/18/19_____

Authorized By:

Luis Marquez

QC Supervisor

Verified By:

_____ Q.C. SUPERVISOR   3/22/19
Name,　　　　　Title,　　　　　Date

FRM-0-0083

1/12/12