TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

Mfg. Date: 3-26-19 Lot# 9032647 PSR-9000 FLX03G LDI Warranty Ends: 9-26-19 MANUFACTURING **PROPERTY TEST METHOD SPECIFICATION** RESULT VISCOSITY Toki Sangyo RE100U Viscometer After mixing: 160 - 200 ps 17 | ps 5 rpms @ 25°C THIXOTROPIC INDEX Toki Sangyo RE100U Viscometer After mixing: 1.0 - 1.3 Viscosity ratio: 5 rpm / 50 rpm microns FINENESS OF GRIND TAI-0-0002 25 microns or less. VISUAL EXAMINATION Microscopic examination: 1. 1-mil drawdown of wet film No bubbles, pits, voids, Passed W particles, color differences. **Passed** 2. Wet film drawdown on No bubbles, pits, voids, particles, color differences. grind gauge **SCREENABILITY Passed** Visual inspection of screen No surface defects, printed panel such as bubbles, pinholes, etc. **TACK-DRY** TY **Passed** Hot air convection oven Tack-free to the touch 80°C / 30 minutes **IMAGING** ORC HMW 680GW - 7 kW Stouffer 21 step: 7 - 9 100 mj/sq cm² (Under Artwork) (clear on copper) Horizontal Developer - 1% Na2CO3 30°C (86°F) / 60 secs., 28 psi RESISTANCE TO 260°C (500°F) / 10 sec x 1 cycle Passed No discoloration, peeling, **SOLDERING** (*) Rosin-based flux or blistering **SOLVENT** Immersion in PM Acetate **Passed** No swelling, softening, **RESISTANCE** (*) 20°C / 20 mins. or blistering 3 H PENCIL HARDNESS (*) TAI-0-0020 3H or greater ADHESION (*) **Passed** TAI-0-0021 100/100 on copper

(*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven.

Verified B	y:		1 1	
- H.	Q.C.	SUPERVISOR	3/29/19	
Name,		Title,	Date	