

TAIYO AMERICA, INC.  
 2675 Antler Drive, Carson City, NV 89701  
 Phone: (775) 885-9959 Fax: (775) 885-9972

**CERTIFICATE OF ANALYSIS and CONFORMANCE**

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

This product meets all the requirements of IPC-SM-840E Classes H and T and Bellcore (Telecordia) GR-78-CORE and is UL recognized 94V-0 (File #E166421, UL Name: PSR-9000AC).

PSR-9000 FXT White


Lot # 9071217

Mfg. Date: 7-12-19  
 Warranty Ends: 4-12-20

<u>PROPERTY</u>	<u>TEST METHOD</u>	<u>MANUFACTURING SPECIFICATION</u>	<u>RESULT</u>
<b>VISCOSITY</b>	Toki Sangyo RE100U Viscometer 5 rpms @ 25° C	Before mixing: Report Only After mixing: 140 - 180 ps	158 ps 149 ps
<b>FINENESS OF GRIND</b>	TAI-0-0002	15 microns maximum	5 microns
<b>VISUAL EXAMINATION</b>	Microscopic examination:		
	1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed <input checked="" type="checkbox"/>
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed <input checked="" type="checkbox"/>
<b>RESISTANCE TO SOLDERING (*)</b>	260° C (500° F) / 10 sec x 1 cycle Rosin-based flux	No discoloration, peeling, or blistering	Passed <input checked="" type="checkbox"/>
<b>FLEXIBILITY (*)</b>	TAI-0-0025	No cracking	Passed <input checked="" type="checkbox"/>
<b>ADHESION (*)</b>	TAI-0-0021	100/100 on copper	Passed <input checked="" type="checkbox"/>

(\*) - Final cure for these tests was 60 minutes @ 150° C (302° F) in a convection oven.

Verified By:

 Q.C. SUPERVISOR 7/17/19  
 Name, Title, Date