TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

PSR-4000MP Blue	Lot#1102237	Mfg. Date: 10-22-2 Warranty Ends: 10-22	-1 -22
PROPERTY VISCOSITY	TEST METHOD Toki Sangyo RE100U Viscometer 5 rpms @ 25°C	MANUFACTURING SPECIFICATION Before mixing: 350 - 400 ps After mixing: 140 - 180 ps	RESULT 386 ps 子 ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	After mixing: 1.2 - 1.6	1.5
FINENESS OF GRIND	TAI-0-0002	20 microns maximum	5 microns
VISUAL EXAMINATION	Microscopic examination: 1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed
	Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed
SCREENABILITY	Visual inspection of screen printed panel	No surface defects, such as bubbles, pinholes, etc.	Passed 🗹
TACK-DRY	Hot air convection oven 80°C / 30 minutes	Tack-free to the touch	Passed 2
IMAGING	ORC HMW 680GW - 7 kW 300 mJ / cm ² (under artwork) Horizontal Developer - 1% Na2CO3 30°C (86°F) / 60 secs., 28 psi	Stouffer 21 step: 8 - 12 (clear on copper)	.9
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 10 sec x 3 cycles Rosin-based flux	No discoloration, peeling, or blistering	Passed D
SOLVENT RESISTANCE (*)	Immersion in PM Acetate 20°C/30 mins.	No swelling, softening, or blistering	Passed U
PENCIL HARDNESS (*)	TAI-0-0020	7H or greater	r 171
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed [4]

(*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven

Verified By:

Title,

Date

FRM-0-0117