

TAIYO AMERICA, INC.  
 2675 Antler Drive, Carson City, NV 89701  
 Phone: (775) 885-9959 Fax: (775) 885-9972

**CERTIFICATE OF ANALYSIS and CONFORMANCE**

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

This product meets all the requirements of IPC-SM-840E Classes H and T and Bellcore (Telecordia) GR-78-CORE and is UL recognized 94V-0 (file #E166421, UL Name: PSR-4000MP).

|            |               |                         |
|------------|---------------|-------------------------|
| PSR-4000MP | Lot # 1120627 | Mfg. Date: 12-06-21     |
|            |               | Warranty Ends: 12-06-22 |

| <u>PROPERTY</u>                    | <u>TEST METHOD</u>   | <u>MANUFACTURING SPECIFICATION</u>                        | <u>RESULT</u>                                    |
|------------------------------------|--|---|--|
| <b>VISCOSITY</b>                   | Toki Sangyo RE100U Viscometer<br>5 rpms @ 25°C   | Before mixing: 350 - 400 ps<br>After mixing: 140 - 180 ps | 376 ps<br>160 ps                                 |
| <b>THIXOTROPIC INDEX</b>           | Toki Sangyo RE100U Viscometer<br>Viscosity ratio: 5 rpm / 50 rpm   | After mixing: 1.2 - 1.6                                   | 1.3  |
| <b>FINENESS OF GRIND</b>           | TAI-0-0002   | 20 microns maximum  | 12.5 microns                                     |
| <b>VISUAL EXAMINATION</b>          | Microscopic examination:   |   |  |
|                                    | 1. 1-mil drawdown of wet film  | No bubbles, pits, voids, particles, color differences.    | Passed <input checked="" type="checkbox"/>       |
|                                    | 2. Wet film drawdown on grind gauge  | No bubbles, pits, voids, particles, color differences.    | Passed <input checked="" type="checkbox"/>       |
| <b>SCREENABILITY</b>               | Visual inspection of screen printed panel  | No surface defects, such as bubbles, pinholes, etc.       | Passed <input checked="" type="checkbox"/>       |
| <b>TACK-DRY</b>                    | Hot air convection oven<br>80°C / 30 minutes   | Tack-free to the touch                                    | Passed <input checked="" type="checkbox"/>       |
| <b>IMAGING</b>                     | ORC HMW 680GW - 7 kW<br>300 mJ / cm <sup>2</sup><br>Horizontal Developer - 1% Na2CO3<br>30°C (86°F) / 60 secs., 28 psi | Stouffer 21 step: 8 - 12<br>(clear on copper)             | 11   |
| <b>RESISTANCE TO SOLDERING (*)</b> | 260°C (500°F) / 10 sec x 3 cycles<br>Rosin-based flux  | No discoloration, peeling, or blistering                  | Passed <input checked="" type="checkbox"/>       |
| <b>SOLVENT RESISTANCE (*)</b>      | Immersion in PM Acetate<br>20°C / 30 mins.   | No swelling, softening, or blistering                     | Passed <input checked="" type="checkbox"/><br>9H |
| <b>PENCIL HARDNESS (*)</b>         | TAI-0-0020   | 7H or greater   |  |
| <b>ADHESION (*)</b>                | TAI-0-0021   | 100/100 on copper   | Passed <input checked="" type="checkbox"/>       |

(\*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven

Verified By:  
 \_\_\_\_\_  
 Name, Title, Date