## TAIYO AMERICA, INC.

## 2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

## CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

This product meets all the requirements of IPC-SM-840E Classes H and T and Bellcore (Telecordia) GR-78-CORE and is UL recognized 94V-0 (File #E166421, UL Name: PSR-4000BN).

PSR-4000BN (DG)	Lot# 1041517	Mfg. Date: H-15-2 Warranty Ends: H-15-	122
PROPERTY VISCOSITY	TEST METHOD  Toki Sangyo RE100U Viscometer 5 rpms @ 25°C	MANUFACTURING SPECIFICATION  Before mixing: 325 - 375 ps  After mixing: 175 - 225 ps	RESULT 363 ps 206 ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	After mixing: 1.2 - 1.6	1.4
FINENESS OF GRIND	TAI-0-0002	15 microns maximum	5 microns
VISUAL EXAMINATION	Microscopic examination:		
	1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed 👿
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed [7]
SCREENABILITY	Visual inspection of screen printed panel	No surface defects, such as bubbles, pinholes, etc.	Passed 📝
TACK-DRY	Hot air convection oven 80°C / 30 minutes	Tack-free to the touch	Passed 🗹
IMAGING	ORC HMW 680GW - 7 kW 500 mJ / cm <sup>2</sup>	Stouffer 21 step: 9 - 13 (clear on copper)	11
	Horizontal Developer - 1% Na2CO3 30°C (86°F) / 60 secs., 28 psi		
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 10 sec x 3 cycles Rosin-based flux	No discoloration, peeling, or blistering	Passed [1]
SOLVENT	Immersion in PM Acetate	No swelling, softening,	Passed V
RESISTANCE (*)	20°C/30 mins.	or blistering	
PENCIL HARDNESS (*)	TAI-0-0020	7H or greater	9 H
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed [V

(\*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven

Name. Title, Date