TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

This product meets all the requirements of IPC-SM-840E Classes H and T and Bellcore (Telecordia) GR-78-CORE and is UL recognized 94V-0 (File #E166421, UL Name: PSR-4000JA).

PSR-4000 LDI (US)	Lot# 1101127	Mfg. Date: しりー いーン Warranty Ends: 4ール	-1 -2-2	
PROPERTY VISCOSITY	TEST METHOD Toki Sangyo RE100U Viscometer 5 rpms @ 25°C	MANUFACTURING SPECIFICATION Before mixing: Report Only After mixing: 220 - 270 ps	<u>RESI</u> ५। 6 २५।	ULT ps ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	After mixing: Report Only	1.5	
FINENESS OF GRIND	TAI-0-0002	5 microns maximum	5	microns
VISUAL EXAMINATION	Microscopic examination:			
	1. I-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed	U
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed	Ū
SCREENABILITY	Visual inspection of screen printed panel	No surface defects, such as bubbles, pinholes, etc.	Passed	g
TACK-DRY	Hot air convection oven 80°C / 30 minutes	Tack-free to the touch	Passed	Ø
IMAGING	ORC HMW 680GW - 7 kW 100 mJ / cm ²	Stouffer 21 step: 12 - 16 (clear on copper)	13	
	Horizontal Developer - 1% Na2CO3 30°C (86°F) / 60 secs., 28 psi			
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 30 sec x 1 cycle Rosin-based flux	No discoloration, peeling, or blistering	Passed	교 .
SOLVENT	Immersion in PM Acetate	No swelling, softening,	Passed	ГŦ
RESISTANCE (*)	20°C / 20 mins.	or blistering	9 H	ت
PENCIL HARDNESS (*)	TAI-0-0020	6H or greater	1 51	
ADHESION (*)	. TAI-0-0021	100/100 on copper	Passed	

(*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven

Verified By:

H. O.C. SUPERVISOR 10/13/21

Name, Title, Date