TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

This product meets all the requirements of IPC-SM-840E Classes H and T and Bellcore (Telecordia) GR-78-CORE.

UVR-150 TU Green	Lot# 1041247	Mfg. Date: リー(2 - 3 Warranty Ends: リー(-1 2-22
PROPERTY VISCOSITY	TEST METHOD Toki Sangyo RE100U Viscometer 5 rpms @ 25°C	MANUFACTURING SPECIFICATION 120 - 140 ps	RESULT
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	1.3 – 1.9	1.7
FINENESS OF GRIND	TAI-0-0002	17.5 microns maximum	12.5 microns
VISUAL EXAMINATION	Microscopic examination: 1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed [1]
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed
SCREENABILITY	Visual inspection of coated panel	No surface defects, such as bubbles, pinholes, etc.	Passed 🗹
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 10 sec x 3 cycles Rosin-based flux	No discoloration, peeling, or blistering	Passed [V
SOLVENT RESISTANCE (*)	Immersion in PM Acetate 20°C/30 mins.	No swelling, softening, or blistering	Passed 🔽
PENCIL HARDNESS (*)	TA1-0-0020	4H or greater	5 H
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed 🛂 .

(*) – UV cure for these test was 1.0 joules/cm² as measured by a ORC UV-350 radiometer using three high pressure mercury vapor lamps @ 80 w/cm.

Verified By:

When the supervisor 4/15/21

Name, Title, Date

FRM-0-0145