## TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

## **CERTIFICATE OF ANALYSIS and CONFORMANCE**

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

This product meets all the requirements of IPC-SM-840E Classes FH and FT.

PSR-9000 LDI Green	Lot#0100927	Mfg. Date: しゅっつう = Warranty Ends: ペーツ	20	
PROPERTY VISCOSITY	TEST METHOD  Toki Sangyo RE100U Viscometer 5 rpms @ 25°C	MANUFACTURING SPECIFICATION Before mixing: Report Only After mixing: 140-200 ps	RESU 243	LT ps ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	After mixing: Report Only	1.3	
FINENESS OF GRIND	TAI-0-0002	5 microns maximum	5	microns
VISUAL EXAMINATION	Microscopic examination:			
	1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed	
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed	
SCREENABILITY	Visual inspection of screen printed panel	No surface defects, such as bubbles, pinholes, etc.	Passed	V
TACK-DRY	Hot air convection oven 80°C / 30 minutes	Tack-free to the touch	Passed	
IMAGING	ORC HMW 680GW - 7 kW 100 mJ/cm <sup>2</sup> (Under Artwork)	Stouffer 21 step: 12 - 16 (clear on copper)	14	
	Horizontal Developer - 1% Na2CO3 30°C (86°F) / 60 secs., 28 psi			
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 10 sec x 3 cycles Rosin-based flux	No discoloration, peeling, or blistering	Passed	d
SOLVENT RESISTANCE (*)	Immersion in PM Acetate 20°C/30 mins.	No swelling, softening, or blistering	Passed	V
FLEXIBILITY (*)	TAI-0-0025	No cracking	Passed	V.
PENCIL HARDNESS (*)	TAI-0-0020	3H or greater	711	
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed	V

(\*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven

Name,	Ti	tle,	Date	
#		SUPERVISOR	(10)	119/20
Verified By:				