## TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

## CERTIFICATE OF CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

PSR-4000 GEC50	Lot# 1051837	Mfg. Date: $5 - 18 - \lambda$ Warranty Ends: $(1 - 18)$	1 -21	
PROPERTY VISCOSITY	TEST METHOD  Toki Sangyo RE100U Viscometer 5 rpms @ 25°C	MANUFACTURING SPECIFICATION Before mixing: 250 - 310 ps After mixing: 150 - 180 ps	159	ULT ps ps
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	Before mixing: 1.1 - 1.5 After mixing: 1.1 - 1.4	1.3	
FINENESS OF GRIND	TAI-0-0002	5 microns maximum	5	microns
VISUAL EXAMINATION	Microscopic examination: 1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed	ď
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed	Ø
SCREENABILITY	Visual inspection of screen printed panel	No surface defects, such as bubbles, pinholes, etc.	Passed	Ø
TACK-DRY	Hot air convection oven 80°C / 30 minutes	Tack-free to the touch	Passed	
IMAGING	ORC HMW 680GW - 7 kW 300 mJ / cm <sup>2</sup> Horizontal Developer - 1% Na2CO3 30°C (86°F) / 60 secs., 28 psi	Report Only (clear on copper)	9	
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 30 sec x 1 cycle Rosin-based flux	No discoloration, peeling, or blistering	Passed	I I
SOLVENT RESISTANCE (*) PENCIL HARDNESS (*)	Immersion in PM Acetate 20°C / 20 mins. TAI-0-0020	No swelling, softening, or blistering 7H or greater	Passed 9 14	ت
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed	

(\*) - Final cure for these tests was 60 minutes @ 150 °C (302 °F) in a convection oven

Verified By:

H. A.C. SUPERVISOR 6/1/21

Name Title, Date

FRM-0-0146

1/28//09