## TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

## CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

PSR-4000 CR01MW	Lot# 1070217	Mfg. Date: そー 0 ユー Warranty Ends: しし 0	21 2-21
PROPERTY VISCOSITY	TEST METHOD  Toki Sangyo RE100U Viscometer  5 rpms @ 25°C	MANUFACTURING SPECIFICATION  After mixing: 150 - 200 ps	RESULT
THIXOTROPIC INDEX	Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm	After mixing: 1.00 - 1.50	1.31
FINENESS OF GRIND	TAI-0-0002	15 Microns or less.	5 microns
VISUAL EXAMINATION	Microscopic examination: 1. 1-mil drawdown of wet film	No bubbles, pits, voids, particles, color differences.	Passed 👩
	2. Wet film drawdown on grind gauge	No bubbles, pits, voids, particles, color differences.	Passed U
SCREENABILITY	Visual inspection of screen printed panel	No surface defects, such as bubbles, pinholes, etc.	Passed U
TACK-DRY	Hot air convection oven 80°C / 30 minutes	Tack-free to the touch	Passed 🕡
IMAGING	ORC HMW 680GW - 7 kW 600 mJ / cm <sup>2</sup> Horizontal Developer - 1% Na2CO3	Stouffer 21 step: Report Only (clear on copper)	į l
TO TO COME A STATE OF THE	30°C (86°F) / 60 secs., 28 -32 psi.		
RESISTANCE TO SOLDERING (*)	260°C (500°F) / 10 sec x 3 cycles Rosin-based flux	No discoloration, peeling, or blistering	Passed 🗹
SOLVENT RESISTANCE (*)	Immersion in PM Acetate 20°C / 30 mins.	No swelling, softening, or blistering	Passed
PENCIL HARDNESS (*)	TAI-0-0020	4H or greater	6H ·
ADHESION (*)	TAI-0-0021	100/100 on copper	Passed 🗾

(\*) - Final cure for these tests was 60 minutes @ 150°C (302°F) in a convection oven

Verified By	γ: Φ, C.	Supervisor	7/7/21
Name,		itle, Da	