TAIYO AMERICA, INC.

2675 Antler Drive, Carson City, NV 89701 Phone: (775) 885-9959 Fax: (775) 885-9972

CERTIFICATE OF ANALYSIS and CONFORMANCE

This is to certify that the following product has been inspected prior to sale and shipment, and complies with Taiyo America's manufacturing specifications for this product.

This product meets all the requirements of IPC-SM-840E Classes H and T and Bellcore (Telecordia) GR-78-CORE and is UL recognized 94V-0 (File #E166421, UL Name: PSR-4000JA).

PSR-4000 LDI (US) Blue

FRM-0-0197

Luis Marquez

QC Supervisor

Lot# 3071417

Mfg. Date: 7 - 14 - 23Warranty Ends: 1 - 14 - 24

9/16/13

			MANUFACTUR	RING				
<u>PROPERTY</u> VISCOSITY		TEST METHOD Toki Sangyo RE100U Viscometer 5 rpms @ 25°C		<u>SPECIFICATION</u>		RESULT		
				Before mixing: Report Only		4.18 ps		
				After mixing: 220 - 270 ps		248 ps		
THIXOTROPIC INDEX		Toki Sangyo RE100U Viscometer Viscosity ratio: 5 rpm / 50 rpm		After mixing: Report	Only	1.4		
FINENESS OF GRIND		TAI-0-0002		5 microns maximum		5	microns	
VISUAL EXAMINATION		Microscopic examination:						
		1. 1-mil drawdown of wet film		No bubbles, pits, voids, particles, color differen			Ø	
		2. Wet film drawdown on grind gauge		No bubbles, pits, voids, particles, color differences.		Passed		
SCREENABILITY		Visual inspection of screen printed panel		No surface defects, such as bubbles, pinholes, etc.		Passed	U	
TACK-DRY		Hot air convection oven 80°C / 30 minutes		Tack-free to the touch		Passed		
IMAGING		ORC HMW 680GW - 7 kW 100 mJ / cm ²		Stouffer 21 step: 12 - 1 (clear on copper)	16	13		
		Horizontal Developer - 1% Na2CO3 30°C (86°F) / 60 secs., 28 psi		(and a sopport		•		
RESISTANCE TO SOLDERING (*)		260°C (500°F) / 30 sec x 1 cycle		No discoloration, peeling,		Passed	□.	
		Rosin-based flux					ت	
SOLVENT RESISTANCE (*)		Immersion in PM Acetate		No swelling, softening,		Passed	Γq	
		20°C / 20 mins.	C / 20 mins.		or blistering		ت	
PENCIL HARDNESS (*)			•	6H or greater		8 H		
ADIADION (NTY EXTENSION		100/100 on copper		Passed	ष	
	Final cure Final cure Final cure America Quality Control department and has been granted a warranty extension. Warranty period ends: 03/14/24 Authorized By:			0 0			پ	
(*) - Final cure			50°C (302°F) in a convection oven					
				Verified By:				
					Surgar	ERVISOR 7/17/23		
				Name.	Title.	Da		
				1 161HLV)	11116,	אַע	110	